

TECHNICAL SPECIFICATION



CONSTRUCTION

MACHINE GAUGE	
PILE HEIGHT	ISO 1766
TUFT DENSITY	ISO 1763
PILE WEIGHT	
TOTAL CARPET WEIGHT	ISO 8543
CARPET THICKNESS	ISO 1765
WIDTH	

LEVEL

5/32nd Loop
4 mm
84,319 tufts/m ²
1,017 gms/m ²
30 oz/yd ²
1,954 gms/m ²
7.1mm
4 & 5 metre

TEXTURED

5/32nd Loop
4.7 mm
84,319 tufts/m ²
1,017 gms/m ²
30 oz/yd ²
1,954 gms/m ²
7.5 mm
4 & 5 metre



COMPOSITION

PILE CONTENT	ISO 1833
PRIMARY BACKING	
SECONDARY BACKING	

100% Wool
Woven Polypropylene
Woven Secondary

100% Wool
Woven Polypropylene
Woven Secondary



PERFORMANCE

SUITABILITY	
WIRA ABRASION TEST	PD 6527: Clause 17
STATIC LOADING	ISO 3416
DYNAMIC LOADING	ISO 2094
TUFT ANCHORAGE	ISO 4919

Extra Heavy Domestic/Medium Contact
Exceeds 12,700 Rubs
13% Thickness Loss after 24 hrs recovery
21.1% Thickness Loss after 1,000 impacts
Above 1kg

Extra Heavy Domestic / Medium Contract
Exceeds 50,000 Rubs
17.8% Thickness loss after 24 hrs recovery
23.9% Thickness loss after 1,000 impacts
Above 1kg



COLOUR FASTNESS

LIGHT FASTNESS	ISO 105-B02
WET FASTNESS	ISO 105-E01
SHAMPOO FASTNESS	BS 1006: UK-TB

3/4 on all colours
5 on all colours
5 on all colours

3/4 on all colours
4/5 on all colours
4/5 on all colours



THERMAL VALUE

TOG VALUE	ISO 5085-1
THERMAL RESISTANCE	

1 Tog
0.1 m ² k/w

1.23 Tog
0.12 m ² k/w



FLAMMABILITY

CE

CE MARK RATING	
HOT METAL NUT TEST	BS4790
METHENAMINE PILL TEST	ISO 6925

Cfl, S1
Pass - Low radius of ignition
Pass

Cfl, S1
Pass - Low radius of ignition
Pass



CHEMICAL IMPACT

CE

FORMALDEHYDE	
REACH CERTIFICATE	

E1
Compliant

E1
Compliant



BIOLOGICAL ATTACK

MOTH / INSECT RESISTANT	
-------------------------	--

Eulan Treated

Eulan Treated



ANTI STATIC

- 0.1 kv (Requirement less than +2.0 kv)
--

- 0.1 kv (Requirement less than +2.0 kv)
--

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. Loop pile carpets should be vacuumed with a cylinder cleaner or suction head only. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear. These areas will appear lighter or shaded in comparison to the less

frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Occasionally wool may contain traces of the sheep's natural environment. These traces can be easily removed and do not effect the durability of the carpet. Joins in loop pile carpet can sometimes be visible, especially so in patterned loop pile. The use of seaming cement is advisable.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.